



POLIFIL® GFPPCC-WS DATA SHEET

DOING THE NEEDFUL SINCE 1973

Chemically Coupled Glass-Reinforced Polypropylene Certified to NSF/ANSI Standard 61 (Black, White, or Natural)

Polifil® GFPPCC-WS series compounds are Water Safe Homopolymer polypropylenes reinforced with chemically coupled glass fibers and are certified to NSF/ANSI Standard 61 and meet the regulatory requirements of the U.S. and Canada for Drinking Water System Components. These compounds offer superior strength and stiffness, improved elevated temperature performance, better creep resistance, higher impact strength and higher resistance to high temperature water than conventional glass fiber reinforced polypropylenes. These compounds are used in chemical resistance applications, appliances, electrical components, automotive, irrigation, utility, filter systems, and potable water products. Standard processing techniques are applicable. Use this information as a guide to aid you in selecting the proper resin for your application.

You can find more information on NSF certification in the Compliance Section of TPG's Website.

PHYSICAL	ASTM/ Method	Polifil® GFPPCC -1005WS	Polifil® GFPPCC -2005WS	Polifil® GFPPCC -3005WS	Polifil® GFPPCC -4005WS
Ash content (%)	D 2584	10	20	30	40
Specific gravity	D 792	0.98	1.04	1.13	1.22
Melt flow 230/2.16 (g/10 min)	D 1238	5.0	5.0	5.0	5.0
Water absorption, 24 hours (%)	D 570	0.03	0.03	0.03	0.03
Mold shrinkage 0.098" wall (in/in)					
Flow Direction	D 955	0.006	0.004	0.004	0.003
Crossflow Direction	D 955	0.011	0.010	0.009	0.008
MECHANICAL @ 73°F					
Tensile strength @ yield (psi)	D 638	6,600	9,500	11,600	13,800
Elongation @ break (%)	D 638	6.8	5.5	4.5	4.0
Flexural modulus, tangent (kpsi)	D 790	390	510	790	980
Flexural strength @ yield (psi)	D 790	9,500	13,500	15,400	17,800
Izod, notched @ R.T. (ft-lbs/in)	D 256	1.2	1.5	1.6	1.9
THERMAL					
Deflection temperature, 66psi (°F)	D 648	285	300	310	315
Deflection temperature, 264psi (°F)	D 648	255	270	290	300

The property values listed above have been obtained using laboratory controlled test methods. They are offered without guarantee since conditions under which the product is used are beyond our control. Mold shrinkage is intended as a guide only, as specific shrinkage is affected by part design, mold design and molding conditions. Therefore, The Plastics Group disclaims any liability for loss or damage incurred in connection with the use of this product. Not to be used for specification purposes.

The Plastics Group of America

Manufacturing/Offices: 1112 River St, Woonsocket, RI 02895 · Tel (401) 765-1000 · Fax (401) 767-2823 · www.plasticsgroup.com

Warehouse and Manufacturing: 84 Fairmount Street, Woonsocket, RI 02895 · www.84fairmount.com